



# CLING WHITE GLOSS

0.145 mm

**Material Description** Static white gloss cling film (without adhesive).  
Easy in application and easy to remove and reusable without leaving a trace on the application surface.

Sticks static on all kind of glossy surfaces. (Sticks because of two identical smooth surfaces)

- Qualifications**
- Gloss White static adhesive soft vinyl
  - Both sides applicable!
  - Easily removable (without a trace)
  - Can be repositioned several times
  - Outdoor compatible
  - Mechanical resistant

**Details** Both side applicable. However, preferred application side is connected to the release liner .  
Always clean surface with soap. When humidity is very dry, clean application surface and apply directly.  
Best application surface is glass, car enamel, PET, PETG smooth plastic.

Shrinkage: 1 minute after separation from release liner. Machine direction . 4% transversal +1%

- Applications**
- Window advertising
  - Short term use
  - Special labels
  - Special POS
  - Promotion labels
  - Indoor durable signs and displays.
  - Exhibitions

<b>Physical Properties</b>	Quality	Static PVC
	Thickness	0.145 mm
	Thickness + Release liner	0.40 mm
	Total Weight + Release liner	325 g/m <sup>2</sup>
	Print side	Gloss white
	Reverse side	Release liner
	Surface tension	34 dynes/cm
	Plasticizer	36% (stabilisation cadmium free)

- Compatibility**
- Nur**  
**Vutek**  
**Hewlett Packard**  
**Roland**  
**Mimaki**  
**Mutoh**  
**And more**
- Eco Solvent
  - Solvent
  - Latex
  - UV-curable
  - UV-curable Led
  - Water
  - Oil
  - Dye-sublimation

Make your own practical test to be sure it reaches your quality standard.  
For all- and latest information see our Compatibility List.

**Printing guidelines** Max. temperature (material) should not exceed 70°C as overheating can impair the flatness of the media. Ink restrictions and heater settings have to be set for specific printer ink combinations to obtain the best results.

**Colour profiles** AT graphix develops high quality ICC colour profiles for the divers printing media's.  
We work with specialists that can do profiling for almost every printer - rip combination.

**Storage conditions** 1 year under normal conditions (10. 25°C at a relative humidity of 30. 75 %). Higher humidity and/or temperature can affect the product performance. Always store the media in a dark place.

**Environment** The media and final prints can be disposed of as vinyl waste. Material is suitable for recycling. Please consult local recycle resources. For treatment of ink or ink residue, please refer to your printer manual or supplier.

Data presented in this product information serve only as a guide-line for compatibility and use. ATgraphix will assume no liability in connection with any use of this information. Technical specifications are subjected to change without prior notice. ATgraphix Vianen, The Netherlands. www.atgraphix.com